

# Blackout Film

## OPTICAL & SOLAR PROPERTIES

	Single Pane
Visible Light Transmitted	0 %
Visible Light Reflected (Int)	
Visible Light Reflected (Ext)	6 %
Ultra Violet Block	100 %
Total Solar Energy Reflected	41 %
Total Solar Energy Transmitted	0 %
Total Solar Energy Absorbed	59 %
Emissivity (Room Side)	0.72
Glare Reduction	100 %
Shading Coefficient	0.20
Solar Heat Gain Coeff. (G-Value)	0.16
U-Value Winter (IP)	0.98
U-Value Winter (SI)	5.57
Luminous Efficacy	0.00
Total Solar Energy Rejected	84 %

R06930S -Blackout Film Pressure Sensitive Adhesive

Ed-D DS No 1800 August 2011