

12 mil Clear

MECHANICAL PROPERTIES

| | |
|---------------------------|-------------|
| Thickness | 12 mil |
| Tensile Strength at Break | 28,500 PSI |
| Break Strength | 336 lb/inch |
| Elongation at Break | 125 % |
| Peel Strength | 7 lb/inch |

OPTICAL & SOLAR PROPERTIES

| | 3mm Single |
|----------------------------------|------------|
| Visible Light Transmitted | 87% |
| Visible Light Reflected (Int) | 11% |
| Visible Light Reflected (Ext) | 11% |
| Ultra Violet Block | 99% |
| Total Solar Energy Reflected | 10% |
| Total Solar Energy Transmitted | 78% |
| Total Solar Energy Absorbed | 12% |
| Glare Reduction | 3% |
| Shading Coefficient | 0.94 |
| Solar Heat Gain Coeff. (G-Value) | 0.82 |
| U-Value Winter (IP) | 1.07 |
| U-Value Winter (SI) | 6.07 |
| Total Solar Energy Rejected | 18% |

R32303T PS

SAFETY ACCREDITATIONS

| | | |
|-------------|--|---------------------------------|
| Impact | EN 356 P2A | ✓ |
| | DIN 52290 Part 4, A1 | ✓ |
| Wind Debris | ASTM E330 | ✓ |
| | TAS 201, 202, 203 Florida Building Code (Dade County Small Missile Test) Hurricane | ✓ |
| Bomb Blast | Siach Gefen IDF testing | ✓x2 + No-Bar |
| | UL 972 Burglary Resisting Glazing Material | ✓ |
| | GSA Level D (4 psi, 30psi/msec) | ✓(3A) x2 + No-Bar on both sides |

Ed-E DS No 1261, March 2012

safety & security

